


Article number: 0.E Test number: 4 Mean Count: Nec 20
 1/2/3/4/5 LOT:225 (FIKSAJLI) 20/1 DK
 Tests: 5/ 500 v = 400 m/min. FV = 14.76 cN

TestCounter: 7.4M
 TesterNo: 4716-xxxx

USTER QUALITY REPORT



Color key: Tests 1 2 3 4 5

B-force	Elongation	Tenacity	B-work
[cN]	[%]	[cN/tex]	[cN.cm]

Overall results: (total)

5 Tests / 2500 Single tests				
Mean values	375.7	5.96	12.72	613.9
CV%	7.94	7.60	7.94	13.41
s +/-	29.8	0.45	1.01	82.3
Q95% +/-	1.2	0.02	0.04	3.2
Max values	476.8	7.20	16.15	912.0
Min values	274.7	4.46	9.30	339.7
P0.01: (0)				
P0.05: (1)	274.7	4.46	9.30	339.7
P0.1 : (2)	277.6	4.48	9.40	352.7
P0.5 : (12)	296.6	4.74	10.05	404.2
P1.0 : (25)	304.0	4.79	10.29	419.9

Weak points (0cN,) F = 0

Overall results: (between)

CV%	2.06	2.93	2.06	2.56
s +/-	7.7	0.17	0.26	15.7

Stil O.E Örnek ID 02248 Nom. numara Nec 20 Nom. büküm
Testler 5 / 1 v= 400 m/min t= 1 min Ölçüm yarığı 3 Kısa elyaf

Tablo

Artikel SCHLAFHORST Materyal sinifi Iplik Maki. Nr. 4-DK
IG 1/2/3/4/5 LOT:225 (FIKSAJLI)

Toplam testler : 5 / 5 Tek test(ler)

Nr	U%	CVm	CVm 3m	CVm 10m	DR 1.5m 5%	İnce -40%	İnce -50%	Kalin +35%	Kalin +50%	Neps +200%	Neps +280%	Rel Num ±
	%	%	%	%	%	/km	/km	/km	/km	/km	/km	%
1	10.34	13.04	2.83	2.05	18.2	137.5	2.5	350.0	25.0	45.0	0.0	-0.7
2	10.58	13.35	3.26	2.06	20.0	102.5	2.5	375.0	35.0	82.5	7.5	-1.8
3	10.39	13.11	2.92	2.06	18.9	125.0	2.5	332.5	35.0	72.5	7.5	0.4
4	10.43	13.18	3.05	2.17	20.1	132.5	2.5	395.0	25.0	152.5	15.0	2.9
5	10.83	13.65	3.32	2.16	21.9	225.0	2.5	420.0	22.5	110.0	2.5	-0.8
Ortalama	10.51	13.27	3.08	2.10	19.8	144.5	2.5	374.5	28.5	92.5	6.5	-0.0
CV	1.9	1.8	6.9	2.7	7.06	32.5	0.0	9.3	21.1	44.1	88.5	1.8
Q95	0.25	0.30	0.26	0.07	1.7	58.3	0.0	43.3	7.5	50.7	7.1	2.3
Max	10.83	13.65	3.32	2.17	21.9	225.0	2.5	420.0	35.0	152.5	15.0	2.9
Min	10.34	13.04	2.83	2.05	18.2	102.5	2.5	332.5	22.5	45.0	0.0	-1.8